


J CAP PROFILES

ARCHITECTURAL ALUMINUM J CAPS - FOR .3125" TO .750" MATERIAL

Our aluminum J caps have a high resistance to corrosion and are easy to machine, cut, form or weld. All our extruded aluminum J channels have a high strength-to-weight ratio, are resistant to stress cracks, and are non-magnetic.

- Stocked in Lengths: Varies by individual profile
- Stocked in Finishes: Varies by individual profile
- Composition: Varies by individual profile




ITEM NUMBERS & DIMENSIONS

| ITEM | A | B | C | D | ALLOY |
|---------------------|-------|-------|-------|-------|--------------------|
| JCP-402 (E-402) | 0.313 | 0.375 | 0.448 | 0.875 | 6560-T42 / 6063-T5 |
| JCP-814 (E-814) | 0.340 | 0.375 | 0.420 | 0.875 | 6063-T6 |
| JCP-5240 (E-5240) | 0.375 | 0.375 | 0.527 | 0.875 | 6063 ALLOY |
| JCP-400 (E-400) | 0.375 | | 0.516 | 0.750 | 6463-T5 |
| JCP-2465 (E-2465) | 0.390 | 0.438 | 0.495 | 0.906 | 6063-T5 |
| JCP-1998 (E-1998) | 0.500 | 0.375 | 0.664 | 1.000 | 6063-T5 |
| JCP-2627 (EAM-2627) | 0.500 | 0.500 | 0.650 | 1.500 | 6063-T6 |
| JCP-3520 (EAM-3520) | 0.500 | 0.500 | 0.650 | 1.500 | 6063-T6 |
| JCP-2207 (EAM-2207) | 0.750 | 0.250 | 1.125 | 1.625 | 6063-T5 |
| JCP-2560 (E-2560) | 0.750 | 0.500 | 0.895 | 1.250 | 6063-T6 |
| JCP-2231 (EAM-2231) | 0.875 | 0.312 | 1.055 | 1.000 | 6063-T6 |

FINISH OPTIONS

Eagle Aluminum offers a variety of standard finishes as well as customized anodized finishes to help create the exact look you need. Custom aluminum finishes are available in anodized, mechanical, or painted finishes.

STANDARD ANODIZED FINISHES



Clear Satin AB1010
Champagne AB1020
Golden Bronze AB1030
Light Bronze AB1040
Medium Bronze AB1050
Dark Bronze AB1060
Deep Bronze AB1070
Black AB1080

POWDER COAT FINISHES



White PM5210
Cream PM5220
Almond PM5230
Khaki PM5240
Silver Gray PM5250
Light Gray PM5260
Dark Gray PM5270
Medium Bronze PM5050
Dark Bronze PM5060
Black PM5080

FIELD PAINTING INSTRUCTIONS

Clean and prep mill finish (MF) trim in accordance with the paint manufacturer's best practices. Ensure paint and primer is recommended for aluminum via paint manufacturer. Apply coating until desired finish is achieved.

Painting Clear Anodized: This is generally not recommended, but can be achieved when necessary. Clean and treat aluminum with an acid etch solution. Rinse thoroughly and dry. Apply an acid-etched primer/primer based on the paint manufacturer's best practices. Apply paint coating per paint manufacturer's specifications.

CUTTING INSTRUCTIONS

When necessary, cut material using a miter saw with a high-quality, non-ferrous carbide blade with a minimum tooth count of 80, and lubricant. Clean trim prior to installation. Refer to saw blade manufacturer's best practices for additional information.

WARRANTY

Eagle Aluminum's warranty covers manufacturing defects for a period of three years. Refer to Eagle Aluminum's warranty documentation for additional details.